




	PetraSlate® Tile & Stone	PetraSlate Tile & Stone 4355 Monaco St. Unit B Denver CO 80216 www.petraslate.com (303) 280-9595	
---	---	---	---

Old World Grey

	Size: 75 x 150 mm		
	Thickness: 7,4 mm		
	Cod. PT02953	2020	

CHARACTERISTICS	Dimensions			STANDARD
	7cm≤N<15cm	N≥15cm		
	(mm)	(%)	(mm)	
SIZE AND APPEARANCE				
LENGTH AND WIDTH				
Admissible deviation in % of the average dimension of a single tile from the manufacturing dimension	±0,75mm	±0,5%	±2,0 mm	EN ISO 10545-2
THICKNESS				
Percent admissible deviation of the average thickness of a single tile from the manufacturing thickness.	±0,5mm	±10%	±0,5mm	EN ISO 10545-2
STRAIGHTNESS OF EDGES				
Admissible deviation of the maximum single value in %with reference to the manufacturing dimension.	±0,5mm	±0,3%	±1,5 mm	EN ISO 10545-2
SQUARENESS				
Admissible deviation of the maximum single value in %with reference to the manufacturing dimension.	±0,75mm	±0,5%	±2 mm	EN ISO 10545-2
FLATNESS				
Central curvature relative to the diagonal calculated with the manufacturing dimension.	´+0,75mm ´-0,5mm	´+0,5% ´-0,3%	´+2,0mm ´-1,5mm	EN ISO 10545-2
Lateral curvature relative to the manufacturing dimension.	´+0,75mm ´-0,5mm	´+0,5% ´-0,3%	´+2,0mm ´-1,5mm	EN ISO 10545-2
Warp relative to the with the diagonal calculate with the manufacturing dimension	±0,75mm	±0,5%	±2,0 mm	EN ISO 10545-2
PHYSICAL PROPERTIES				
WATER ABSORTION				

% weight	Average > 10% if more than 20% must be indicated by manufacturer.	EN ISO 10545-3
BREAKING STRENGTH (N)		
Thickness ≥ 7,5mm	> 600 N	EN ISO 10545-4
Thickness <7,5mm	>200 N	EN ISO 10545-4
BENDING STRENGTH		
Thickness ≥ 7,5mm	>12N/mm ²	EN ISO 10545-4
Thickness <7,5mm	Mín. indiv. 15 N/m ²	EN ISO 10545-4
THERMAL SHOCK RESISTANCE	Satisfy	EN ISO 10545-9
CRAZING RESISTANCE	Satisfy	EN ISO 10545-11
ADHESIVES		
Cementitious adhesives	>0,5N/mm ²	EN 12004:2007 +A1:2012, 4.1
FIRE REACTION	Class A1	–
CHEMICAL PROPERTIES		
STAIN RESISTANCE	> class 3	EN ISO 10545-14
CHEMICAL RESISTANCE		
Acid and alkali resistance of low concentration.	>GLB	EN ISO 10545-13
Acid and alkali resistance of high concentration.	>GHB	EN ISO 10545-13
Resistance to domestic products and salt for pools.	>GB	EN ISO 10545-13
DANGEROUS SUBSTANCES EMISSION		
a) Lead (en mg/dm ²)	>0,1mg/dm ²	EN ISO 10545-15
b) Cadmium (en mg/dm ²)	>0,1mg/dm ²	EN ISO 10545-15
DURABILITY	Satisfy	–